



18 x 7 (19 x 7)



FIBER CORE			Regular nominal diameter	STEEL CORE			
Approx. weight	Minimum breaking load [kN]			Approx. weight	Minimum breaking load [kN]		
	1770	1960			1770	1960	
[Kg/m]	[N/mm ²]		[mm]	[Kg/m]	[N/mm ²]		
0.195	28.4	31.5	7	0.200	28.4	31.5	
0.252	37.2	41.1	8	0.249	37.2	41.1	
0.315	47.0	52.1	9	0.319	47.0	52.1	
0.407	58.1	64.3	10	0.398	58.1	64.3	
0.469	70.2	77.8	11	0.496	70.2	77.8	
0.569	83.6	92.6	12	0.599	83.6	92.6	
0.680	98.1	109	13	0.675	98.1	109	
0.760	114	126	14	0.766	114	126	
1.021	149	165	16	1.038	149	165	
1.118	168	186	17	1.138	168	186	
1.254	188	208	18	1.256	188	208	
1.362	210	232	19	1.381	210	232	
1.502	232	257	20	1.591	232	257	
1.829	281	311	22	1.866	281	311	
2.178	334	370	24	2.270	334	370	
2.366	363	402	25	2.423	363	402	
2.513	392	435	26	2.597	392	435	
2.919	455	504	28	3.066	455	504	
3.361	523	579	30	3.445	523	579	
3.828	594	658	32	3.985	594	658	
4.245	671	743	34	4.416	671	743	
4.792	752	833	36	5.025	752	833	

TECHNICAL DATA:

Total number of strands: 18 / 19

Total number of wires: 126 / 133

Core type : WSC

Outer strands construction: 1 – 6

Outer strands number: 12

Lay type: regular lay

Non-rotating wire rope with great flexibility

ON REQUEST OPTIONS:

Galvanized / ungalvanized

Lang Jay type

Lang lay type
Left hand lay

Left hand lay

Greasing level

Standard: EN, ISO, DIN

Five | June 2013

For order please contact

Tel : +40 244 598052

Fax : +40 244 598632

CĂRȚI ROMÂNEȘC



PLOIESTI – ROMÂNIA

Certified by:

